

NYCOA 5033 HST

33% Glass-Fiber Reinforced, Heat Stabilized, Translucent Nylon 66 Resin.

NYCOA 5033 HST is a 33% glass fiber reinforced, heat stabilized, translucent Nylon 66 resin used for injection molding. It has been specifically formulated for see through storage tanks for automotive fluids.

NYCOA 5033 HST has excellent chemical resistance to most greases, oils and other hydrocarbons, high thermal resistance and translucency.

Typical automotive under the hood applications include reservoir bottles for brake oil, transmission fluid, engine coolant, and power steering fluid. It also finds application in fuel tanks for ATVs, lawn & garden equipment and handheld machines.

Property	Method	English		SI	
		Unit	Value	Unit	Value
Physical Properties					
Specific Gravity	D 792	-	1.38	-	1.38
Water Absorption, 24 hr	D 570	%	0.7	%	0.7
Linear Mold Shrinkage (Parallel)	D 955	%	0.5	%	0.5
Linear Mold Shrinkage (Normal)	D 955	%	0.8	%	0.8
Mechanical Properties					
Hardness, Rockwell (R Scale)	D 785	-	122	-	122
Tensile Strength	D 638	psi	29,008	MPa	200
Ultimate Elongation	D 638	%	4	%	4
Flexural Modulus	D 790	psi	1,290,838	MPa	8,900
Flexural Strength	D 790	psi	37,710	MPa	260
Notched Izod Impact	D 256	ft.lbs./in.	2.6	J/m	130
Unnotched Izod Impact	D 256	ft.lbs./in.	20	J/m	1000
Thermal Properties					
Melting Temperature	D 789	°F	505	°C	263
Heat Deflection Temp, 66 psi (0.45 Mpa)	D 648	°F	500	°C	260
Heat Deflection Temp, 264 psi (1.82 Mpa)	D 648	°F	464	°C	240

All test specimens tested in "dry" state – less than 0.3% moisture.
Izod Impact – ½" x ¼" bars.
All tensile properties obtained at a testing speed of 2 in./min.

The information contained herein is based upon data believed to be thoroughly reliable. However, due to the many uses to which this material is put, and the different equipment and techniques used, we cannot guarantee results in specific instances. Nor should any statement herein be construed as a recommendation to use our products in the infringement of a patent.